



Polypropylene (PP)

## BURPOLEN HM 6525 BLACK

### Product Description

BURPOLEN HM 6525 BLACK is a %20 mineral modified polypropylene.

Recycle Content: %100 (PCR)

Properties	Unit	Test Method	Value
Physical properties			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	1.04 - 1.09
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	6 - 16
Ash Content	%	ISO 3451	18 - 22
Mechanical properties			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	25 - 35
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	10 - 20
Flexure modulus (2mm/min) (23°C)	MPa	ISO 178	2000 - 2500
Impact			
Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 3.5

### Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

### Processing Techniques

BURPOLEN HM 6525 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

### Storage

The BURPOLEN®HM 6525 BLACK in pellet form is packed in bigbag (1000 Kg).