



Polypropylene (PP)

# BURPOLEN PP GFR 30 BLACK

## Product Description

BURPOLEN PP GFR 30 BLACK is a %30 glass fiber modified polypropylene.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	1,10 - 1,16
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	7 - 14
Ash Content (750 °C - 1h)	%	ISO 3451	27 - 33

## Mechanical properties

Flexural modulus (2mm/min) (23°C)	MPa	ISO 178	≥ 5500
Flexural Strength (2mm/min) (23°C)	MPa	ISO 178	≥ 40

## Impact

Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 9
----------------------------	-------------------	---------	-----

## Hardness

Hardness (23°C)	Shore D	ISO 868	≥ 72
-----------------	---------	---------	------

## Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

## Processing Techniques

BURPOLEN PP GFR 30 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

## Storage

The BURPOLEN® PP GFR 30 BLACK in pellet form is packed in bigbag (1000 Kg).