



Polypropylene (PP)

## BURPOLEN C300 BLACK

### Product Description

BURPOLEN C300 BLACK is a %30 CaCO<sub>3</sub> filled polypropylene.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	1,12 - 1,16
Melt Flow Rate, (230 °C/2.16 kg)	g/10min	ISO 1133	3 - 10
Ash Content	%	ISO 3451	27 - 33
<b>Mechanical properties</b>			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	10 - 15
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	25 - 30
Flexural modulus (2mm/min) (23°C)	MPa	ISO 178	1000 - 1800
<b>Impact</b>			
Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	4 - 10

### Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

### Processing Techniques

BURPOLEN C300 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

### Storage

The BURPOLEN® C300 BLACK in pellet form is packed in bigbag (1000 Kg).