



Polypropylene (PP)

# BURPOLEN 2013 T13 BLACK

## Product Description

BURPOLEN 2013 T13 BLACK is a %13 mineral modified polypropylene.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	0.97 - 1.01
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	20 - 25
Ash Content	%	ISO 3451	10 - 15
<b>Mechanical properties</b>			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	≥ 18
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	≥ 10
Flexural modulus (2mm/min) (23°C)	MPa	ISO 178	1500 - 2250
<b>Impact</b>			
Notched IZOD Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 5

## Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

## Processing Techniques

BURPOLEN 2013 T13 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

## Storage

The BURPOLEN<sup>®</sup> 2013 T13 BLACK in pellet form is packed in bigbag (1000 Kg).