



Polypropylene (PP)

BURPOLEN C1509 IM BLACK

Product Description

BURPOLEN C1509 IM BLACK is an unfilled and high impact copolymer.

Properties	Unit	Test Method	Value
Physical properties			
Density, (23 °C)	g/cm ³	ISO 1183	0.90 – 0.96
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	12 - 20
Ash Content	%	ISO 3451	≤ 5
Mechanical properties			
Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	18 - 24
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	≥ 25
Tensile modulus (1mm/min) (23°C)	MPa	ISO 527	800 - 1000
Impact			
Notched Izod Impact (23°C)	kJ/m ²	ISO 180	≥ 20

Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

Processing Techniques

BURPOLEN C1509 IM BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

Storage

The BURPOLEN® C1509 IM BLACK in pellet form is packed in bigbag (1000 Kg).