



Polypropylene (PP)

## BURPOLEN H0505 BLACK

### Product Description

BURPOLEN H0505 BLACK is a reinforced homopolymer.

Properties	Unit	Test Method	Value
<b>Physical properties</b>			
Density, (23 °C)	g/cm <sup>3</sup>	ISO 1183	0.90 – 0.96
Melt Flow Rate, (230 °C/2.16 kg)	g/10 min	ISO 1133	5 - 10
Ash Content	%	ISO 3451	0 - 7

### Mechanical properties

Tensile Stress at Yield,(50mm/min) (23°C)	MPa	ISO 527	20 - 30
Tensile Strain at Break,(50mm/min) (23°C)	%	ISO 527	10 - 15
Flexure modulus (2 mm/min) (23°C)	MPa	ISO 178	1300 - 1700

### Impact

Notched Izod Impact (23°C)	kJ/m <sup>2</sup>	ISO 180	≥ 4
----------------------------	-------------------	---------	-----

### Notes

The properties are typical, non-binding mean values found for injection moulded natural test bars. Pigments and other modifications may alter these values.

### Processing Techniques

BURPOLEN H0505 BLACK is easy to process with standard injection moulding machines.

Drying	°C	2hr- 4hr	80 – 90 °C
--------	----	----------	------------

### Storage

The BURPOLEN® H0505 BLACK in pellet form is packed in bigbag (1000 Kg).